# **FERROXCUBE**

# DATA SHEET

TX9.7/4.8/3.2 Alloy powder toroids

New data 2008 Sep 01



# Alloy powder toroids

TX9.7/4.8/3.2

## **RING CORES (TOROIDS)**

## **Effective core parameters**

SYMBOL	PARAME	VALUE	UNIT	
Σ(I/A)	core factor (C1)	2.90	mm <sup>-1</sup>	
V <sub>e</sub>	effective volume		164	mm <sup>3</sup>
l <sub>e</sub>	effective length		21.8	mm
A <sub>e</sub>	effective area		7.52	mm <sup>2</sup>
m	mass of core	MPP	1.40	g
	(for μ <sub>i</sub> 125)	Sendust	1.01	g
		High-Flux	1.30	g


#### Coating

The cores are coated with epoxy. The colour is black (Sendust), grey (MPP) or khaki (High-Flux). Maximum operating temperature is 200 °C. Parylene coating is also available (transparent, maximum operating temperature 130 °C).

#### Isolation voltage

AC isolation voltage: 1000 V (Parylene: 750 V). Contacts are applied on the edge of the ring core, which is also the critical point for the winding operation.

**Ring core data - Note** 1. Mechanical dimensions : OD  $\leq$  10.29, ID  $\geq$  4.27, H  $\leq$  3.81



GRADE	A <sub>L</sub> (nH)	μί	B (mT) at	CORE LOSS (W) at	
			H = 100 kA/m; f = 10 kHz; T = 25 °C	f = 100 kHz; B = 100 mT; T = 25 °C	TYPE NUMBER
MPP	6 ± 8 %	14	≥ 640	0.246	TX9.7/3.2-M2-A6
<u> </u>	11 ± 8 %	26	≥ 700	0.197	TX9.7/3.2-M2-A11
	25 ± 8 %	60	≥ 760	0.123	TX9.7/3.2-M2-A25
	53 ± 8 %	125	≥ 800	0.123	TX9.7/3.2-M2-A53
	63 ± 8 %	147	≥ 800	0.131	TX9.7/3.2-M2-A63
	68 ± 8 %	160	≥ 800	0.131	TX9.7/3.2-M2-A68
	74 ± 8 %	173	≥ 800	0.131	TX9.7/3.2-M2-A74
<u> </u>	84 ± 8 %	200	≥ 800	0.246	TX9.7/3.2-M2-A84
<u> </u>	128 ± 8 %	300	≥ 800	0.246	TX9.7/3.2-M2-A128
Sendust (1)	25 ± 12 %	60	≥ 1030	0.140	TX9.7/3.2-S7-A25-MC
<u> </u>	32 ± 12 %	75	≥ 1040	0.140	TX9.7/3.2-S7-A32-MC
<u> </u>	38 ± 12 %	90	≥ 1050	0.140	TX9.7/3.2-S7-A38-MC
<u> </u>	53 ± 12 %	125	≥ 1060	0.140	TX9.7/3.2-S7-A53-MC
High-Flux	6 ± 8 %	14	≥ 890	0.410	TX9.7/3.2-H2-A6
<u> </u>	11 ± 8 %	26	≥ 980	0.328	TX9.7/3.2-H2-A11
<b> </b>	25 ± 8 %	60	≥ 1280	0.295	TX9.7/3.2-H2-A25
<b> </b>	53 ± 8 %	125	≥ 1370	0.328	TX9.7/3.2-H2-A53
<b> </b>	63 ± 8 %	147	≥ 1385	0.361	TX9.7/3.2-H2-A63
-	68 ± 8 %	160	≥ 1400	0.574	TX9.7/3.2-H2-A68

2008 Sep 01 1818

# Alloy powder toroids

TX9.7/4.8/3.2

#### **DATA SHEET STATUS DEFINITIONS**

DATA SHEET STATUS	PRODUCT STATUS	DEFINITIONS
Preliminary specification	Development	This data sheet contains preliminary data. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.
Product specification	Production	This data sheet contains final specifications. Ferroxcube reserves the right to make changes at any time without notice in order to improve design and supply the best possible product.

### **DISCLAIMER**

**Life support applications** — These products are not designed for use in life support appliances, devices, or systems where malfunction of these products can reasonably be expected to result in personal injury. Ferroxcube customers using or selling these products for use in such applications do so at their own risk and agree to fully indemnify Ferroxcube for any damages resulting from such application.

#### **PRODUCT STATUS DEFINITIONS**

STATUS	INDICATION	DEFINITION	
Prototype	prot	These are products that have been made as development samples for the purposes of technical evaluation only. The data for these types is provisional and is subject to change.	
Design-in	des	These products are recommended for new designs.	
Preferred		These products are recommended for use in current designs and are available via our sales channels.	
Support	sup	These products are <b>not</b> recommended for new designs and may not be available through all of our sales channels. Customers are advised to check for availability.	

2008 Sep 01 1819